

Numerical Study of a System of Long Josephson Junctions with Inductive and Capacitive Couplings

I. R. Rahmonov^{1,2,a}, Yu. M. Shukrinov^{1,3,b}, A. Plecenik^{4,c}, E. V. Zemlyanaya^{3,5,d}, and M. V. Bashashin^{3,5,e}

¹BLTP, Joint Institute for Nuclear Research, 141980 Dubna, Russia

²Umarov Physical and Technical Institute, Dushanbe, Tajikistan

³Dubna International University for Nature, Society and Man, Dubna, Russia

⁴Department of Experimental Physics, Comenius University, Bratislava, Slovakia

⁵LIT, Joint Institute for Nuclear Research, 141980 Dubna, Russia

Abstract. The phase dynamics of the stacked long Josephson junctions is investigated taking into account the inductive and capacitive couplings between junctions and the diffusion current. The simulation of the current–voltage characteristics is based on the numerical solution of a system of nonlinear partial differential equations by a fourth order Runge–Kutta method and finite-difference approximation. A parallel implementation is based on the MPI technique. The effectiveness of the MPI/C++ code is confirmed by calculations on the multi-processor cluster CICC (LIT JINR, Dubna). We demonstrate the appearance of the charge traveling wave (CTW) at the boundary of the zero field step. Based on this fact, we conclude that the CTW and the fluxons coexist.

1 Introduction

The layered high-temperature superconducting materials such as $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_{8+\delta}$ (BSCCO) can be considered as a stack of coupled intrinsic Josephson junctions (JJ) [1]. This system is one of the promising objects of superconducting electronics [2, 3]. Coherent terahertz electromagnetic radiation from this system provides wide possibilities for various applications [4]. However, the mechanism of this radiation is still unclear. The most intense coherent radiation corresponds to the region of the current–voltage characteristic (CVC) where switching from the upper branch to inner branches occurs [3]. In this region of the CVC the Josephson oscillations excite a longitudinal plasma wave due to the parametric resonance [5]. In stacked long Josephson junctions (SLJJ) with the length L larger than the Josephson penetration depth λ_J ($L > \lambda_J$) the parametric resonance can be realized in the zero field step region [6, 7] of the CVC and the fluxons coexist with the longitudinal plasma wave, which can be interpreted as the collective excitation [8]. Other types of the collective states [9] in the stack of coupled JJs are the Josephson plasma [10] and the charge traveling wave (CTW) [11] along

^ae-mail: rahmonov@theor.jinr.ru, ilhom-tj@inbox.ru

^be-mail: shukrinov@theor.jinr.ru

^ce-mail: pleceni@fmph.uniba.sk

^de-mail: elena@jinr.ru

^ee-mail: bashashinmv@jinr.ru

the stack. A stack of coupled JJs can be considered as a laboratory for the study of the collective excitations in superconducting nanostructures. First of all, the investigation of the long JJs stack is an actual problem, because most of the experimental results were obtained for this system. Therefore, the construction of a model that ensures an adequate description of the properties of the SLJJ in the high temperature superconductors is one of the topical tasks of the modern physics of the superconductivity and, also, an actual problem is the construction of effective numerical algorithms for the simulation of the phase dynamics of the SLJJ.

To describe the SLJJ, Sakai, Bodin, and Pedersen [12] proposed a model taking into account the inductive coupling between JJs. Machida and Sakai [13] proposed a generalization of the model to the case of both inductive and capacitive coupling. However, they disregarded the diffusion current [14], the significance of which was emphasized in [15]. Furthermore, the CVC have not yet been studied within the generalized Machida–Sakai model.

In this paper, we investigate the phase dynamics of the SLJJ taking into account the inductive and capacitive couplings [12, 13] and the diffusion current [15]. Simulation is based on a numerical solution of a system of nonlinear partial differential equations by a fourth order Runge–Kutta method, finite-difference approximation, and the MPI technique for parallel implementation. The effectiveness of the MPI/C++ code is confirmed by calculations on the multi-processor cluster CICC (LIT JINR, Dubna).

2 Theoretical model and numerical approach

We use the model with inductive and capacitive couplings [12, 13] and with the diffusion current [15]. The SLJJ has a layered structure with $N + 1$ superconducting and interjacent insulating layers. The x -axis is directed along the length L , the y -axis along the width of the superconducting layers and the z -axis is perpendicular to the superconducting layers. Each superconducting layer is described by the Ginzburg–Landau order parameter $\Delta_l = |\Delta_0| \exp(i\theta_l)$. The l -th and the $(l - 1)$ -th superconducting layers form the l -th JJ and it is described by the gauge–invariant phase difference (1) of the Ginsburg–Landau order parameter [13]

$$\varphi_l = \theta_l - \theta_{l-1} - \frac{2e}{\hbar c} \int_{z_{l-1}}^{z_l} A_z dz, \quad (1)$$

where θ_l is the phase of the order parameter of the l -th superconducting layer, e is the electrical charge, \hbar is the Plank constant, c is the speed of the light in vacuum and A_z is the vector potential. The system of equations which describes the phase dynamics of the coupled long JJs stack in terms of normalized quantities can be written as follows:

$$\begin{cases} \frac{\partial \varphi_l}{\partial t} = D_C V_l + s_C V_{l+1} + s_C V_{l-1}, \\ \frac{\partial V_l}{\partial t} = \sum_{k=1}^N \mathcal{L}_{lk}^{-1} \frac{\partial^2 \varphi_k}{\partial x^2} - \sin \varphi_l + \beta \frac{\partial \varphi_l}{\partial t} + I, \end{cases} \quad (2)$$

where $D_C = 1 + (2\lambda_e/d_l) \coth(d_s/\lambda_e)$, λ_e -the Debye screening length, d_l and d_s denote the thickness of the insulating and the superconducting layers, $s_C = -\lambda_e/[d_l \sinh(d_s/\lambda_e)]$ is the capacitive coupling parameter, V_l is the voltage of the l -th JJ normalized to $V_0 = \hbar\omega_p/(2e)$, $\omega_p = \sqrt{8\pi d_l e j_c}/(\hbar\epsilon)$ is the plasma frequency of JJ, j_c is the critical current of JJ, ϵ is the dielectric constant of the insulating layer, $\beta = \sigma V_0/d_l j_c$ is the dissipation parameter, σ is the conductance of the JJ, I is the bias current normalized to the critical current j_c . Here \mathcal{L} is the matrix of the inductive coupling.

$$\mathbf{f} = \begin{pmatrix} 1 & S & 0 & \dots & & & & S \\ S & 1 & S & 0 & \dots & & & \\ 0 & S & 1 & S & 0 & \dots & & \\ \vdots & \vdots \\ & & & \dots & 0 & S & 1 & S \\ S & & & & \dots & 0 & S & 1 \end{pmatrix},$$

where $S = s_L/D_L$, $D_L = d_l + 2\lambda_L \coth(d_s/\lambda_L)$ is the effective magnetic thickness, λ_L is the London penetration depth and $s_L = -\lambda_L/\sinh(d_s/\lambda_L)$ is the parameter of the inductive coupling. In the system of equations (2) the time is normalized to the reverse ω_p and the coordinate x – to the Josephson penetration depth λ_J . The initial conditions for the system of equations (2) are $\varphi_l(x,0) = 0$ and $V_l(x,0) = 0$. The coordinate derivative of the phase difference at the boundaries is equal to the external magnetic field $\partial\varphi_l(0,t)/\partial t = \partial\varphi_l(L,t)/\partial t = B_{\text{ext}}$.

The main tasks are to calculate the CVC, the spatio-temporal dependence of the magnetic field in the JJs, and the electric charge in the superconducting layers. First of all, we should solve numerically the system of partial differential equations (2). We introduce the uniform mesh with the stepsize Δx in the coordinate x along the JJ and the stepsize Δt in time. We put $\Delta t = \Delta x/5$ in accordance with the Courant–Friedrichs–Lewy condition in order to provide the stability of the numerical scheme. We denote the discrete coordinate by $x_i = \Delta x \times (i - 1)$, where $i = 1, \dots, N_x$ and $N_x = L/\Delta x + 1$ is the number of coordinate nodes. The discrete time is denoted by $t_j = \Delta t \times j$, where $j = 0, 1, 2, \dots, N_t$. The $x = 0$ corresponds to x_1 and $x = L$ – to x_{N_x} . In the same way, $t = 0$ corresponds to t_1 and $t = T_{\text{max}}$ to t_{N_t} , where T_{max} is the end of the time domain. The standard second order finite difference approximation in the spatial coordinate x is used,

$$\frac{\partial^2 \varphi_l^1}{\partial x^2} = \frac{2(\varphi_l^2 - \varphi_l^1)}{\Delta x^2} - \frac{2B_{\text{ext}}}{\Delta x}, \quad \frac{\partial^2 \varphi_l^i}{\partial x^2} = \frac{\varphi_l^{i+1} - 2\varphi_l^i + \varphi_l^{i-1}}{\Delta x^2}, \quad \frac{\partial^2 \varphi_l^{N_x}}{\partial x^2} = \frac{2(\varphi_l^{N_x-1} - \varphi_l^{N_x})}{\Delta x^2} + \frac{2B_{\text{ext}}}{\Delta x}.$$

The resulting system of ordinary differential equations is solved numerically for a fixed value of the current I by a 4th-order Runge-Kutta (RK) algorithm (here l is the JJ number) in the interval $[0, L]$ along the x -coordinate and $[0, T_{\text{max}}]$ in time and obtain the $\varphi_l(x, t)$ and $V_l(x, t)$ as functions of x and t . Next, the obtained $V_l(x, t)$ is averaged with respect to the coordinate x using

$$\bar{V}_l(t) = \frac{1}{L} \int_0^L V_l(x, t) dx \tag{3}$$

and with respect to the time t using

$$\langle V_l \rangle = \frac{1}{T_{\text{max}} - T_{\text{min}}} \int_{T_{\text{min}}}^{T_{\text{max}}} \bar{V}_l(t) dt, \tag{4}$$

where T_{min} denotes the beginning of the averaging interval. The total voltage of the JJs stack can be calculated using $\langle V \rangle = \sum_{l=1}^N \langle V_l \rangle$. The integrals (3) and (4) are calculated using the Simpson method and the rectangles method, respectively. Then the bias current value is changed by ΔI and the above procedure is repeated. In the calculations the bias current increases from the start value $I = 0.01$ to $I = I_{\text{max}}$ and then decreases to $I = 0$.

In order to investigate collective excitations in the JJs stack, like the longitudinal plasma wave [5] or charge travelling wave [11], the electric charge–time dependence in the superconducting layers is

Table 1. Simulation time of CVC in minutes per number of processes

P	1	2	4	6	8	10	12
$L = 5, N = 10$	106.2	46.8	27.3	25.7	19.5	14.4	16.7
$L = 10, N = 10$	213	92.5	62.5	44.4	42.3	32.4	37.2
$L = 10, N = 3$	37.1	19.9	11.3	8.6	7.5	6.4	6.4

to be calculated. In this case, the electric charge, normalized to $Q_0 = \varepsilon V_0 / 4\pi d_s d_l$, is calculated as a function of x and t using the expression $Q_l(x, t) = V_l(x, t) - V_{l-1}(x, t)$ [8]. Then the value of $Q_l(x, t)$ is averaged with respect to the coordinate x using the Simpson method. For the external current value corresponding to the fluxon states, the magnetic field B in the JJs is calculated using the expression

$$B_l = \sum_{k=1}^N \mathcal{E}_{lk}^{-1} (\partial \varphi_k / \partial x). \text{ The magnetic field is normalized to } B_0 = \hbar c / 2e D_L \lambda_J.$$

The parallel algorithm is based on a distribution of the calculations in the coordinate nodes x_i between the group of P_m parallel MPI-processes, where $m = 0, 1 \dots, M$. At each time-step t_j , each process P_m calculates the RK coefficients and $V_l(x_i, t_j)$, $\phi_l(x_i, t_j)$ in the nodes $i_{\min} \leq i < i_{\max}$, where $i_{\min} = m \times L_x / M$ and $i_{\max} = (m + 1) \times L_x / M$. At each t_j the exchange between neighbor processes is arranged: each process P_m ($m < M - 1$) sends the RK coefficients and values of V and φ at $i = i_{\max} - 1$ -th point to the P_{m+1} -process; each P_m process ($m > 0$) sends the RK coefficients and solutions at $i = i_{\min}$ to the P_{m-1} -process. In order to calculate the average value V_l , the parallel calculation of the integral (3) is performed at each time-step t_j . Each P_m -process calculates the partial sum of elements $V_l(x_i, t_j)$ at each JJ l in accordance to the Simpson quadrature formula. Then the resulting summation is performed in the process P_0 . In the P_0 -process V_l is averaged in time and in LJJs, and the resulting value is saved to the file. For some values of I the solutions $V_l(x_i, t_j)$ and $\phi_l(t_i, t_j)$ are collected in the process P_0 where they are saved to the file together with the respective physical characteristics.

3 Results and discussions

Let us first of all discuss the effectiveness of the parallel algorithm. The methodical calculations on the CICC multi-processor cluster (LIT JINR) with a different number of parallel MPI-processes are performed. For these calculations we put the number of JJs $N = 10$, the JJ length $L = 5$ and $L = 10$; $\Delta x = 0.05$; $\Delta I = 0.005$. Table 1 shows the calculation time (in minutes) of the CVC per number of processes for the stacks with $N = 3$, $N = 10$ JJs and with length $L = 5$, $L = 10$. One can see that the developed parallel algorithm provides 6-7 times acceleration (depending on the values of N and L) as compared to the sequential simulation.

The next step of the parallel optimization of the long JJs stack simulation code is the parallelization of the calculations at each junction.

Let us now discuss the main features of the single long JJ. Figure 1(a) shows the one loop CVC of the single JJ with $L = 10$. The calculations have been performed for the $\beta = 0.2$, $B_{\text{ext}} = 0$, $\Delta I = 0.0001$ and $T_{\text{max}} = 200$. The stepsize in the coordinate and time were $\Delta x = 0.05$ and $\Delta t = \Delta x / 5$, respectively. The curve shows the hysteresis and seven step structure at decreasing current. These zero-field steps (ZFS) correspond to the formation of fluxons in the JJs [6, 7]. The velocity of the fluxon u is given by the expression [6, 7] $u = [1 + 4\beta/\pi I]^{-1/2}$ and it is given in units of the Swihart velocity $c_j = \omega_p \lambda_J$. Under the condition $u = c_j$, the periodic motion of the fluxon leads to the average voltage $V = 2\pi n u / L$ and the formation of the corresponding step on the CVC. The voltage positions of the steps on the calculated CVC are in good agreement with this expression, which proves the stability of the numerical approach. The appearance of n fluxons in the JJs is accompanied by the appearance




Figure 1. (a) CVC of the single long JJ with $L = 10$; (b) Spatiotemporal dependence of magnetic field in the JJ at $I = 0.76$

of n steps in the CVC [6, 7]. In order to directly demonstrate fluxons, we calculate the spatiotemporal dependence of the magnetic field in JJ. Figure 1(b) shows the time evolution of the spatial distribution of the magnetic field in JJs at the value of current value $I = 0.76$, which corresponds to the 6th ZFS. It indicates the formation of a state with six fluxons.




Figure 2. (a) CVC of stacked long JJs with the length $L = 5$; (b) Charge–time dependence in the right boundary of the third ZFS

Now we discuss the numerical results obtained for the SLJJ. The CVC of the stack with $N = 10$ JJ and $L = 5$ is represented in Fig. 2(a), which demonstrates the hysteresis and three ZFS. In order to study in more detail the collective dynamics of the SLJJ, we have calculated the time dependence of the averaged charge with respect to the x -coordinate in the region of the CVC, corresponding to the third ZFS. This region of the CVC is shown by the hollow arrow in Fig. 2(a). The charge–time dependence is shown in Fig. 2(b). The inset in this figure demonstrates the character of the charge oscillation. Analyzing the numerical results we conclude that, at the boundaries of the third ZFS, a charge traveling wave (CTW) is formed. The resonance between the CTW and the Josephson

oscillations increases the charge amplitude, which can be seen in these figures. Since the CTW appears in the CVC region corresponding to the ZFS, we may conclude about the coexistence of the CTW and the fluxons.

4 Conclusions

In this paper, we have investigated numerically the phase dynamics of the SLJJ taking into account the inductive and capacitive couplings between junctions and diffusion current. In our investigation we used the parallel and sequential calculations of CVC. The parallel implementation is based on the MPI technique. We showed that the parallel algorithm results in a seven time acceleration in comparison with the sequential one. We compared the numerical and theoretical results for a single long JJ and obtained a good agreement. For the case of the SLJJ we demonstrated that, at the boundaries of the zero field step, a charge travelling wave is formed. Based on this fact, we concluded that the CTW and the fluxons coexist. This effect is confirmed by a number of calculations with different values of the LJJ length. Due to the resonance between the CTW and the Josephson oscillations, the charge amplitude in the superconducting layers increases.

Acknowledgements

The reported study was funded by RFBR according to the research projects 15–29–01217 and 15-51-61011, and a 2015 grant of the Plenipotentiary Representative of the Slovak Government at JINR. I.R.R. and Yu.M.S. thank S. Dubnička, M.Hnatič and J.Buša for discussions and support of this work.

References

- [1] R. Kleiner, F. Steinmeyer, G. Kunkel, P. Müller, *Phys. Rev. Lett.* **68**, 2394 (1992)
- [2] A.A. Yurgens, *Supercond.Sci.Technol.* **13**, R85 (2000)
- [3] T.M. Benseman, A.E. Koshelev, K.E. Gray, W.K. Kwok, U. Welp, K. Kadowaki, M. Tachiki, T. Yamamoto, *Phys. Rev. B* **84**, 064523 (2011)
- [4] L. Ozyuzer, A.E. Koshelev, C. Kurter, N. Gopalsami, Q. Li, M. Tachiki, K. Kadowaki, T. Yamamoto, H. Minami, H. Yamaguchi et al., *Science* **318**, 1291 (2007)
- [5] Y.M. Shukrinov, F. Mahfouzi, *Phys. Rev. Lett.* **98**, 157001 (2007)
- [6] D.W. McLaughlin, A.C. Scott, *Phys. Rev. A* **18**, 1652 (1978)
- [7] N.F. Pedersen, D. Welner, *Phys. Rev. B* **29**, 2551 (1984)
- [8] I.R. Rahmonov, Y.M. Shukrinov, A. Irie, *JETP Letters* **99**, 632 (2014)
- [9] R. Kleiner, T. Gaber, G. Hechtfisher, *Phys. Rev. B* **62**, 4086 (2000)
- [10] Y. Matsuda, M.B. Gaifullin, K. Kumagai, K. Kadowaki, T. Mochiku, *Phys. Rev. Lett.* **75**, 4512 (1995)
- [11] Y.M. Shukrinov, M. Hamdipour, *JETP Letters* **95**, 307 (2012)
- [12] S. Sakai, P. Bodin, N.F. Pedersen, *J. Appl. Phys.* **73**, 2411 (1993)
- [13] M. Machida, S. Sakai, *Phys. Rev. B* **70**, 144520 (2004)
- [14] Y.M. Shukrinov, F. Mahfouzi, *Physica C* **434**, 6 (2006)
- [15] Y.M. Shukrinov, I.R. Rahmonov, *JETP* **115**, 289 (2012)