“ Fundamentals of Thermodynamic Modelling of Materials ”

November 15-19, 2010
INSTN – CEA Saclay, France

PROFESSOR & TOPIC

Pavel KORZHAVYI

MSE, KTH, Sweden

*Theoretical data for
assessments*

[03003]

Organized by

Bo SUNDMAN bo.sundman@cea.fr
Constantin MEIS constantin.meis@cea.fr

Theoretical data for assessments

Pavel A. Korzhavyi

Applied Materials Physics
Department of Materials Science and Engineering
School of Industrial Engineering and Management
Royal Institute of Technology (KTH), Stockholm

11/17 2010

A modern CALPHAD flowchart

Success example: NIST-JANAF data for diatomic gases

Oxygen (O₂)

(REFERENCE STATE = IDEAL GAS)

M = 31.9988 O₂ (M₀)

0 to 6000 K Ideal Diatomic Gas

$\Delta_f H^\circ(0 \text{ K}) = 0 \text{ kJ mol}^{-1}$
 $\Delta_f H^\circ(298.15 \text{ K}) = 0 \text{ kJ mol}^{-1}$

S^o(298.15 K) = 205.147 ± 0.035

		Electronic and Molecular constants (n = 2)				Enthalpy Reference Temperature - T ₀ = 298.15 K		Standard State Pressure - p ^o = 6.11 MPa						
		Vibrational												
State	g	T _e , cm ⁻¹	ω _e , cm ⁻¹	Anharmonicity, cm ⁻¹	B _e , cm ⁻¹	ω _e , cm ⁻¹	D _e , cm ⁻¹	β _e , cm ⁻¹	J-K	S ^o - [G ^o - F(T ₀)/T]	H ^o - [H ^o (T ₀)]	Δ ₀ H ^o	Δ ₀ G ^o	log K _r
X ³ Σ _g ⁻	3	0	1580.1932	ω _{x1} 11.580804 ω _{x2} 0.04747736 ω _{x3} -1.272748x10 ⁻⁵	1.445622 6.408450x10 ⁻⁶ -2.846158x10 ⁻⁶	0.01591268 ⁻³			298.15	29.376	205.147	205.147	0.	0.
a ¹ Δ _g	2	7882.39	[1509.3]	ω _{a1} [12.9]	1.4263	0.0171	[4.97x10 ⁻⁷]		300	29.385	205.229	205.148	-8.683	0.
b ¹ Δ _g	1	13120.9085	1432.6661	ω _{b1} 13.9336 ω _{b2} -0.0143	1.4004796 -4.294192x10 ⁻⁵	0.018169303	5.356x10 ⁻⁶	0.077x10 ⁻⁶	350	29.694	209.803	205.506	-5.779	0.
c ³ Σ _g ⁻	1	32664.1	794.29	ω _{c1} 12.736 ω _{c2} -0.2444 ω _{c3} 0.00055	0.9155 -0.000740 [0.014]	0.01391	[10.5x10 ⁻⁷]		430	30.384	217.485	207.330	-2.868	0.
d ¹ Δ _g	6	34319	[750]	ω _{d1} [14]	[0.91]				500	31.091	220.693	208.524	-1.410	0.
A ³ Σ _g ⁻	3	35007.15	799.08	ω _{A1} 12.16 ω _{A2} -0.550 ω _{A3} 10.614080 ω _{A4} -0.059212435 ω _{A5} -0.022974994	0.91053 -0.000097 0.818975 -6.30472x10 ⁻⁴	0.01416 -0.000097 0.0119225	4.79x10 ⁻⁶ -0.10x10 ⁻⁶		600	32.090	226.451	211.044	0.054	0.
B ³ Σ _g ⁻	3	49158.15	709.05770						700	32.981	231.466	213.611	12.499	0.
									800	33.733	235.921	216.126	13.835	0.
									900	34.355	239.931	218.552	19.241	0.
									1000	34.879	243.578	220.875	22.703	0.
									1100	35.300	246.922	223.093	26.212	0.
									1200	35.667	250.010	225.290	29.761	0.
									1300	35.988	252.878	227.229	33.344	0.
									1400	36.277	255.536	229.138	36.937	0.
									1500	36.544	258.068	231.002	40.599	0.
									1600	36.796	260.434	232.768	44.266	0.
									1700	37.040	262.672	234.442	47.938	0.
									1800	37.277	264.796	236.089	51.673	0.
									1900	37.509	266.813	237.713	55.413	0.
									2000	37.741	268.748	239.160	59.175	0.
									2100	37.969	270.595	240.613	62.961	0.
									2200	38.196	272.366	242.063	66.768	0.

Internal degrees of freedom taken into account:

• Vibrational (harmonic and anharmonic)

• Rotational

• Rotation-vibration interactions

• Centrifugal stretching

• Electronic (transitions between molecular terms)

PREVIOUS: March 1977 (1 atm)

CURRENT: March 1977 (1 bar)

Oxygen (O₂)

O₂(ref)

J. Phys. Chem. Ref. Data, Monograph 9

Internal degrees of freedom taken into account:

- **Vibrational (harmonic and anharmonic)**
- **Rotational**
 - **Rotation-vibration interactions**
 - **Centrifugal stretching**
- **Electronic (transitions between molecular terms)**

J. Phys. Chem. Ref. Data, Monograph 9

NIST-JANAF THERMOCHEMICAL TABLES

1745

Slide 3

Theoretical data for assessments

11/17 2010

H₂ molecule

Stable state: Paired spins, symmetric

Unstable state: Unpaired spins, antisymmetric

Slide 4

Theoretical data for assessments

11/17 2010

Vibrational properties of dimer molecules

Fit: $U(r) = C + D \left[\exp \left(-2\alpha \frac{r - r_0}{r_0} \right) - 2 \exp \left(-\alpha \frac{r - r_0}{r_0} \right) \right]$

Slide 5

Theoretical data for assessments

11/17 2010

Vibrational properties of dimer molecules

Spectrum: $E = C - D + \hbar\omega_0 \left(n + \frac{1}{2} \right) - \hbar x\omega_0 \left(n + \frac{1}{2} \right)^2$

Zero-point energy: $ZPE \approx \frac{1}{2} \hbar\omega_0 - \frac{1}{4} \hbar x\omega_0$

Dimer	Data source	r_0 (Å)	ω_0 (cm ⁻¹)	$x\omega_0$ (cm ⁻¹)	ZPE (cm ⁻¹)
¹ H ₂	This work	0.7517	4330.76	155.14	2126.59
	Exp. [1]	0.7414	4401.21	121.34	2179.30
¹⁶ O ₂	This work	1.2294	1560.09	13.22	776.74
	Exp. [1]	1.2075	1580.19	11.98	787.38
⁶³ Cu ₂	This work	2.2149	264.55	1.02	135.14
	Exp. [1]	2.2197	270.89	1.21	
⁶³ Cu ¹ H	This work	1.4557	1941.26	37.51	987.30
	Exp. [1]	1.4626	1995.54	41.90	

[1] K. K. Irikura, *Experimental vibrational zero-point energies: Diatomic molecules*, J. Phys. Chem. Ref. Data **36**, 389 (2007).

Slide 6

Theoretical data for assessments

11/17 2010

Energy units and accuracy

$$1000 \text{ cm}^{-1} \cong 0.124 \text{ eV} \cong 12.0 \text{ kJ/mol}$$

Table 2: Absolute error (eV) of some density functional approximations in predicting the dissociation energy of small molecules [2].

Molecule	LDA	GGA(PBE)	BLYP	PKZB
H ₂	+0.16	-0.21	-0.00	+0.22
O ₂	+2.36	+1.01	+0.64	+0.47
H ₂ O	+1.49	+0.09	+0.01	-0.09
N ₂	+1.69	+0.64	+0.49	+0.03

[2] S. Kurth, J.W. Perdew, and P. Blaha, *Molecular and solid-state tests of density functional approximations: LSD, GGAs, and Meta-GGAs*, Intl. J. Quantum Chem. **75**, 899 (1999).

Slide 7

Theoretical data for assessments

11/17 2010

Accuracy (continued)

- **Accuracy** of DFT functionals **is routinely checked** in molecular and solid-state tests, whenever a new functional is created.
- It is good practice to **find out the accuracy** of various DFT approximations **for your system**.

Some useful references:

[2] S. Kurth, J.W. Perdew, and P. Blaha, *Molecular and solid-state tests of density functional approximations: LSD, GGAs, and Meta-GGAs*, Intl. J. Quantum Chem. **75**, 899 (1999).

[3] P. Haas, F. Tran, and P. Blaha, *Calculation of the lattice constant of solids with semilocal functionals*, Phys. Rev B **79**, 085104 (2009).

[5] L. Pedroza, A.J.R. da Silva, K. Capelle, *Gradient-dependent density functionals of the Perdew-Burke-Ernzerhof type for atoms, molecules, and solids*, Phys. Rev. B **79**, 201106 (2009).

[4] P. Haas, F. Tran, P. Blaha, K. Schwarz, and R. Laskowski, *Insight into the performance of GGA functionals for solid-state calculations*, Phys. Rev. B **80**, 195109 (2009).

[6] P.J. Feibelman, *DFT Versus the "Real World" (or, Waiting for Godft)*, Top. Catal. **53**, 417 (2010).

Slide 8

Theoretical data for assessments

11/17 2010

Phonon spectrum of Cu₂O

P.A. Korzhavyi and B. Johansson, Technical Report TR-10-30, (SKB, Stockholm, 2010).

Slide 9

Theoretical data for assessments

11/17 2010

Thermodynamic properties of Cu₂O

$$E_0 = U_0 + \frac{1}{2} \int_0^\infty \hbar \omega g(\omega) d\omega$$

$$E(T) = E_0 + \int_0^\infty \frac{\hbar \omega g(\omega) d\omega}{\exp(\hbar \omega / k_B T) - 1}$$

$$C_V = k_B \int_0^\infty \left(\frac{\hbar \omega}{2k_B T} \right)^2 \frac{g(\omega) d\omega}{\sinh^2(\hbar \omega / 2k_B T)}$$

$$F(T) = U_0 + k_B T \int_0^\infty \log[2 \sinh(\hbar \omega / 2k_B T)] d\omega$$

Slide 10

Theoretical data for assessments

11/17 2010

Thermodynamic properties of Cu_2O

Slide 11

Theoretical data for assessments

11/17 2010

Thermodynamic properties of Cu_2O

Slide 12

Theoretical data for assessments

11/17 2010

Degrees of freedom to be taken into account in solids

• Atomic defects (non-stoichiometry, high temperature)	Time scale
$> 10^{-6} \text{ s}$
• Vibrational (harmonic and anharmonic)	$\sim 10^{-13} \text{ s}$
• Magnetic excitations	$\sim 10^{-14} \text{ s}$
• Electronic excitations	$\sim 10^{-15} \text{ s}$

Slide 13

Theoretical data for assessments

11/17 2010

Compound energy formalism (CEF)

Slide 14

Theoretical data for assessments

11/17 2010

4-sublattice model, bcc Fe-Ti: $2^4=16$ end members

Slide 15

Theoretical data for assessments

11/17 2010

4-sublattice model, bcc Fe-Ti: enthalpies of formation

Slide 16

Theoretical data for assessments

11/17 2010

A combined *ab initio* - CALPHAD study

P.A. Korzhavyi, B. Sundman, M. Selleby, and B. Johansson, *Atomic, electronic, and magnetic structure of iron-based sigma-phases*, in *Integrative and Interdisciplinary Aspects of Intermetallics*, MRS Proc., **842**, edited by M.J. Mills *et al.*, (Warrendale, 2005), pp. S4.10.1-6.

Slide 17

Theoretical data for assessments

11/17 2010

Crystallographically inequivalent sites

Icosahedrally coordinated sites

M1 (CN=12)

M4 (CN=12)

High coordination number (high-CN) sites

M2 (CN=15)

M3 (CN=14)

M5 (CN=14)

Slide 18

Theoretical data for assessments

11/17 2010

σ -phase model

→ "end member compound": FCCFC = $\text{Fe}_2\text{Cr}_4\text{Cr}_8\text{Fe}_8\text{Cr}_8$

→ $2^5 = 32$ end member compound energies.

These energies have been calculated from first principles

Slide 19

Theoretical data for assessments

11/17 2010

Energies of the end-member compounds

Slide 20

Theoretical data for assessments

11/17 2010

Magnetic moments and entropy contribution

- Magnetic moments are vanishing on Fe atoms occupying icosahedral sites (1,4).
- Magnetic moments are high, $\approx 2 \mu_B$, on Fe atoms occupying high-CN sites (2,3,5).
- Disorder of Fe magnetic moments gives an important contribution to the entropy:

$$S_{\text{magn}} = k_B \sum_s a^{(s)} \cdot c_{Fe}^{(s)} \cdot \ln(M_{Fe}^{(s)} + 1)$$

Slide 21

Theoretical data for assessments

11/17 2010

Isoelectronic sigma phases

	3B	4B	5B	6B	7B	8B		
3d	21 Sc [Ar]4s ² 3d ¹ scandium 44.96	22 Ti [Ar]4s ² 3d ² titanium 47.88	23 V [Ar]4s ² 3d ³ vanadium 50.94	24 Cr [Ar]4s ¹ 3d ⁵ chromium 52.00	25 Mn [Ar]4s ² 3d ⁵ manganese 54.94	26 Fe [Ar]4s ² 3d ⁶ iron 55.85	27 Co [Ar]4s ² 3d ⁷ cobalt 58.93	28 Ni [Ar]4s ² 3d ⁸ nickel 58.69
4d	39 Y [Kr]5s ² 4d ¹ yttrium 88.91	40 Zr [Kr]5s ² 4d ² zirconium 91.22	41 Nb [Kr]5s ¹ 4d ⁴ niobium 92.91	42 Mo [Kr]5s ¹ 4d ⁵ molybdenum 95.94	43 Tc [Kr]5s ² 4d ⁵ technetium (98)	44 Ru [Kr]5s ¹ 4d ⁷ ruthenium 101.1	45 Rh [Kr]5s ¹ 4d ⁸ rhodium 102.9	46 Pd [Kr]4d ¹⁰ palladium 106.4
5d	57 La* [Xe]6s ² 5d ¹ lanthanum 138.9	72 Hf [Xe]6s ² 4f ¹⁴ 5d ² hafnium 178.5	73 Ta [Xe]6s ² 4f ¹⁴ 5d ³ tantalum 180.9	74 W [Xe]6s ² 4f ¹⁴ 5d ⁴ tungsten 183.9	75 Re [Xe]6s ² 4f ¹⁴ 5d ⁵ rhenium 186.2	76 Os [Xe]6s ² 4f ¹⁴ 5d ⁶ osmium 190.2	77 Ir [Xe]6s ² 4f ¹⁴ 5d ⁷ iridium 190.2	78 Pt [Xe]6s ¹ 4f ¹⁴ 5d ⁹ platinum 195.1
N _d =	1	2	3	4	5	6	7	8

Slide 22

Theoretical data for assessments

11/17 2010

Mo-Ru sigma phase

Fig. 1. Calculated enthalpies of formation for the end-member compounds of 5-sublattice model (open circles) and 3 sublattice model (filled circles). Free energies

C.-S. Oh, H. Murakami, and H. Harada, *J. Alloys Compounds* **313**, 115 (2000). O. Grånäs, P.A. Korzhavyi, A.E. Kissavos, and I.A. Abrikosov, *CALPHAD* **32**, 171 (2008).

Slide 23

Theoretical data for assessments

11/17 2010

Non-stoichiometry in titanium carbides and nitrides

- TiC_x and TiN_x crystallize in the B1 (NaCl) structure.
- Vacancies only on the non-metal sublattice, $(\text{Ti})(\text{X},\text{Va})$.

α : hcp
 β : bcc
 δ : fcc
 ϵ : anti-rutile

K. Frisk et al., *Calphad* (2004)

S. Jonsson Z. Metallkunde (1996)

Slide 24

Theoretical data for assessments

11/17 2010

Vacancy-vacancy interactions

Cluster expansion: $E(\sigma) = \sum_f D_f J_f \bar{\Pi}_f(\sigma)$

Theoretical methods:

Connolly-Williams method (CWM)

Generalized perturbation method (SGPM)

Vacancies prefer 3rd nearest neighbor distance, $\langle 1, \frac{1}{2}, \frac{1}{2} \rangle$.

TABLE I. Effective carbon-vacancy interactions in TiC_x (degrees Kelvin). See text for the definitions.

	J_{21}	J_{22}	J_{23}	J_{24}	J_{25}	J_{26}
SGPM	54	181	-10	-1	-12	24
CWM	113	246	-13	-5		
	J_{27}	J_{28}	J_{31}	J_{32}	J_{41}	
SGPM	1	-5	-10	53	-6	
CWM			-33	64	-6	

Short-range order (SRO)

Experiment: T. Priem *et al.* (1989).

Slide 25

Theoretical data for assessments

11/17 2010

Monte Carlo modeling of vacancy ordering

Calculated phase diagram

Order of vacancies in the (111) layers of Ti_3C_2 and Ti_6C_5 :

Ordering pattern

Stacking between layers

P. Korzhavyi *et al.*, Phys. Rev. Lett. **88**, 15505 (2002).

Monte Carlo

- Simulation box: 32x32x32 (32768 carbon sites)
- 5000 time steps per site

Slide 26

Theoretical data for assessments

11/17 2010

MC simulation of the ground state structures in TiN_x

- Ground state ordering is slightly different from TiC_x .
- Stacking of $(011)_{B1}$ planes instead of $(111)_{B1}$.
- All structures can be described within a 24 site unit cell (5 sublattices).
- Calculate the total energy of the structures and compare with the previous model.

GUS L. W. HART, VOLKER BLUM, MICHAEL J. WALORSKI
AND ALEX ZUNGER (Nature Materials, 2005)

Slide 27

Theoretical data for assessments

11/17 2010

CEF models for Ti-TiC-TiN

TiC-type

TiN-type

Slide 28

Theoretical data for assessments

11/17 2010

Prediction of phase diagrams

Calculated and experimental TiC_x stability plot at $\sim 298 \text{ K}$

Ti-C phase diagram

Slide 29

Theoretical data for assessments

11/17 2010

Prediction of phase diagrams

Calculated and experimental TiC_x stability plot at $\sim 298 \text{ K}$

Ti-C phase diagram

Slide 30

Theoretical data for assessments

11/17 2010

Prediction of ternary phase diagrams and short range order

— Ti-C-N at 1423 K

Slide 31

Theoretical data for assessments

11/17 2010