The Jules Horowitz Reactor Research Project: A New High Performance Material Testing Reactor Working as an International User Facility – First Developments to Address R&D on Material

Gilles BIGNAN¹, Christian COLIN¹, Jocelyn PIERRE¹, Christophe BLANDIN¹,
Christian GONNIER¹, Michel AUCLAIR², Franck ROZENBLUM²

¹ CEA-DEN-DER, JHR Project (Cadarache, France)

² CEA-DEN-DRSN, Service d'Irradiations en Réacteurs et d'Etudes Nucléaires, SIREN (Saclay, France)

The Jules Horowitz Reactor (JHR) is a new Material Testing Reactor (MTR) currently under construction at CEA Cadarache research center in the south of France. It will represent a major research infrastructure for scientific studies dealing with material and fuel behavior under irradiation (and is consequently identified for this purpose within various European road maps and forums; ESFRI, SNETP...). The reactor will also contribute to medical Isotope production.

The reactor will perform R&D programs for the optimization of the present generation of Nuclear Power Plants (NPPs), will support the development of the next generation of NPPs (mainly LWRs) and also will offer irradiation capabilities for future reactor materials and fuels.

JHR is fully optimized for testing material and fuel under irradiation, in normal, incidental and accidental situations:

- with modern irradiation loops producing the operational condition of the different power reactor technologies ;
- with major innovative embarked in-pile instrumentation and out-pile analysis to perform high-quality R&D experiments ;
- with high thermal and fast neutron flux capacity and high dpa rate to address existing and future NPP needs.

JHR is funded and steered and will be operate as an international user-facility open to international collaboration. This lead to the following topics:

- the existence of an international consortium gathering the funding organizations to steer the project ;
- the setting-up of an international scientific community around JHR through seminars, working groups to optimize the experimental capacity versus future R&D needs ;
- the preparation of the first JHR International Program potentially open to non-members of the JHR consortium.

It will answer needs expressed by the scientific community (R&D institutes, TSO...) and the industrial companies (utilities, fuel vendors...). Consequently, the JHR facility will become a major scientific hub for cutting edge research and material investigations (multilateral support to complete cost effective studies avoiding fragmentation of scientific effort, access to developing countries to such state of the art research reactor facilities, supra national approach....).

Considering material behavior under irradiation, such studies is most of the time associated with a complex multi-physical modelling of the materials' behaviors. It requires well controlled and instrumented irradiation experiments in material testing reactors.

This paper gives an up-to-date status of the construction (Fig. 1) and of the developments performed to build the future experimental capacity dedicated to the material irradiations in JHR reactor. In-core and in reflector devices will be presented (Fig. 2), corresponding to large ranges of temperature and neutrons flux for the irradiation conditions. A special attention focuses on the improvement of the thermal stability and gradients of the interest zones in samples despite strong gamma heating and on

an improvement of the instrumentation devoted to the experiments. Some specific devices in support of LWR type reactors will be described such as equipment designed for the qualification of Reactor Pressure Vessel (RPV) steels, for the study of the stress corrosion cracking assisted by irradiation phenomena (IASCC), or for the studies of creep-swelling of structural materials.

Fig. 1: General view of the JHR building (September 2015).

Fig. 2: reactor pool (left) and part a reactor block (right) of the JHR (September 2015).

References

- [1] G. Bignan, X. Bravo, "The Jules Horowitz Reactor: A new high performance MTR (Material Testing Reactor) working as an International User Facility in support to Nuclear Industry, Public Bodies and Research Institutes", Nuclear Energy International Journal, December 2014, pp. 26-30.

FROM RESEARCH TO INDUSTRY

cea den

instn

Centre of Excellence for
Nuclear Materials

2nd International Workshop

Irradiation of Nuclear Materials:
Flux and Dose Effects

November 4-6, 2015
CEA – INSTN Cadarache, France

The Jules Horowitz Research Reactor Project

A New High Performance Material Testing Reactor

working as an International Facility:

First Developments to address R&D on Material

G. BIGNAN⁽¹⁾ | C. COLIN⁽²⁾ | J. PIERRE⁽²⁾ | C. BLANDIN⁽²⁾ |
C. GONNIER⁽²⁾ | M. AUCLAIR⁽³⁾ | F. ROZENBLUM⁽³⁾

gilles.bignan@cea.fr ; christian.colin@cea.fr

(1) CEA Cadarache: DEN / DER

(2) CEA Cadarache: DEN / DER / SRJH

(3) CEA Saclay : DEN / DRSN / SIREN

2nd International Workshop MINOS, November 4-6 2015, Cadarache

MTR allows to reproduce on a small scale, real power plant conditions and in some cases, more severe conditions for

Material screening (comparison of materials tested under representative conditions)

Material characterisation (behaviour of one material in a wide range of operating conditions, up to off-normal and severe conditions)

Fuel element qualification (test of one / several fuel rods (clad+fuel))

Motivation of JHR : An Ageing fleet of MTR in Europe

Age of current E.U. main MTRs in 2015 (years)

BR2 (B)	52
HALDEN (N)	55
HFR (NL)	54
LVR 15 (CZ)	58
MARIA (PO)	41
OSIRIS (F)	49

★ Under construction

1) R&D in support to nuclear Industry

- Safety and Plant life time management (ageing & new plants)
- Fuel behavior validation in incidental and accidental situation
- Assess innovations and related safety for future NPPs

2) Radio-isotopes supply for medical application

■ MOI production

JHR will supply 25% of the European demand (today about 8 millions protocols/year) and up to 50% upon specific request

3) A key tool to support expertise

- Training of new generations (JHR simulator, secondees's program)
- Maintaining a national expertise staff and credibility for public acceptance
- **Assessing safety requirements evolution and international regulation harmonisation**

JHR OPERATING RULES

19/03/2007 Signature of the JHR consortium

JHR consortium gathers organizations which take part financially in the construction of JHR (1 representative / organization)

JHR Consortium current partnership: Research centers & Industrial companies

Studsvik

AREVA

EDF

Ciemat
Centro de Investigaciones
Energéticas, Medioambientales
y Tecnológicas

SCK • CEN
STUDIECENTRUM VOOR KERNENERGIE
CENTRE D'ÉTUDE DE L'ÉNERGIE NUCLÉAIRE

cea

VTT

UJV

**पुर्वि
DAE**

IAEC

Associated Partnership

IAEA

**NATIONAL NUCLEAR
LABORATORY**

In some cases, the organization (member of the JHR consortium) is itself the representative of a national domestic consortium which gathers organizations among industry, academics, R&D organizations, TSO, or Safety Authority

Preparing JHR International Community:

- *The yearly seminar*
- *The 3 Working Groups*
- *The Secondee Program*
 - *The recent ICTERR
designation by the IAEA*

JHR International User Facility

Preparing JHR International Community:

- **The yearly scientific and technical seminar:** possible participation for some non-members (5th April 2015-next one embedded with NUGENIA forum-April 2016)

- **3 Working Groups :**
 - Fuel R&D topics
 - Material R&D topics
 - Technology issues for experimental devices

- Compliance between future R&D needs and first experimental capacity
- Preparation of first JHR programs

← **Secondee Program**

- ▶ Create international scientific networks
- ▶ Make available facilities and experience of mature R&D centres in the field of peaceful uses of Nuclear Energy to affiliates
- ▶ Lead innovative joint programs with shared results
- ▶ Host international scientists / engineers
- ▶ Provide “hands on” nuclear education “in the field”

CEA offer within IAEA/ICERR centered on futur JHR and its ancillary facilities

LECI : Hot Lab on Materials

- Hands-On Training (Equipments)
- R&D Projects

ISIS: Education & Training

ORPHEE : Neutron beams

- Hands-On Training (Equipments)
- R&D Projects

EOLE/MINERVE:

- Education & Training
- Hands-On Training
- R&D Projects

JHR : MTR

- Hands-On Training
- R&D Projects

LECA : Hot Lab on Fuel

- R&D Projects
- Hands-On Training (Equipments)

ZEPHYR : LPR

New Projects

Status of JHR project Fall 2015

Removal of dôme formwork

Installation of pre-stressing cables

Installation of specific devices for reactor containment monitoring

REACTOR BLOCK

Beginning of components manufacturing

Machining of bottom plug flange
(S12/2015)

Main vessel

Water Box RPP (S12/2015)

Water Box REP (S18/2015)

Bottom plug shell
(S18/2015)

JHR design and performances

*First fleet of experimental
Devices under development
For Material Investigation*

A facility dedicated to experimental purposes :

■ A modern facility :

- ▶ Large experimental areas
- ▶ Non destructive examination benches
- ▶ Fission Product Laboratory
- ▶ Chemistry Laboratory...

I&C: 3 floors, 490 m²

Cubicle: 3 floors, 700 m²

JHR facility & experimental capacity

A 100 MW High Performances Research Reactor

~20 simultaneous experiments

In reflector

Up to $3.5E14$ n/cm².s (th)

Fixed irradiation positions
($\Phi 100$ mm & $\Phi 200$ mm)
and on 6 displacement systems

LWR fuel
experiments

+

Material ageing
(low ageing rate)

Thermal neutron flux

In core

Up to $5.5E14$ n/cm².s ($E > 1$ MeV)
Up to $1.E15$ n/cm².s ($E > 0.1$ MeV)

7 small locations ($\Phi \sim 32$ mm)
3 large locations ($\Phi \sim 80$ mm)

Material ageing
(up to 16 dpa/y)

Fast neutron flux

Reliable Displacements
Systems for Power adjustment,
Power transient tests...

JHR facility & experimental capacity: First fleet of irradiation material devices

Topic	Objective	Material	Instrumentation	Flux ($n.cm^{-2}.s^{-1}$)	Fluence ($n.cm^{-2}$) / dpa	Temp. ($^{\circ}C$)
Reactor Pressure Vessel	Dose accumulation	Low alloyed steels	Loading	$10^{11} - 10^{13}$	$< 2.10^{20}$	240 – 320
Internals	Dose accumulation	Stainless steels, Ni-based alloys		$10^{12} - 10^{14}$	10 – 80 dpa	320 – 390
	Environment effect		Loading, displacement measurements			
	Mechanical testing		Loading, displacement measurements			
Cladding	Mechanical properties	Zr-alloys SS	Loading, displacement	$< 3. 10^{14}$		$< 400^{\circ}C$
	Accident tolerance

OCCITANE

- Irradiated material behaviour (low dpa rate)
 - ✓ tensile tests, resilience test, crack propagation tests
 - ✓ Behaviour of Thermal affected zones

JHR facility & experimental capacity: First fleet of irradiation material devices

Topic	Objective	Material	Instrumentation	Flux (n.cm ⁻² .s ⁻¹)	Fluence (n.cm ⁻²) / dpa	Temp. (°C)
Reactor Pressure Vessel	Dose accumulation	Low alloyed steels	Loading	10 ¹¹ – 10 ¹³	< 2.10 ²⁰	240 – 320
Internals	Dose accumulation	Stainless steels, Ni-based alloys		10 ¹² – 10 ¹⁴	10 – 80 dpa	320 – 390
	Environment effect		Loading, displacement measurements			
	Mechanical testing		Loading, displacement measurements			
Cladding	Mechanical properties	Zr-alloys SS	Loading, displacement	< 3. 10 ¹⁴		< 400°C
	Accident tolerance					

OCCITANE

OCCITANE

MICA / CALIPSO

MICA / CALIPSO

JHR facility & experimental capacity: First fleet of irradiation material devices

Topic	Objective	Material	Instrumentation	Flux (n.cm ⁻² .s ⁻¹)	Fluence (n.cm ⁻²) / dpa	Temp. (°C)	
Reactor Pressure Vessel	Dose accumulation	Low alloyed steels	Loading	10 ¹¹ – 10 ¹³	< 2.10 ²⁰	240 – 320	OCCITANE
Internals	Dose accumulation	Stainless steels, Ni-based alloys		10 ¹² – 10 ¹⁴	10 – 80 dpa	320 – 390	OCCITANE
	Environment effect		Loading, displacement measurements				CLOE
	Mechanical testing		Loading, displacement measurements				MICA / CALIPSO
Cladding	Mechanical properties	Zr-alloys SS	Loading, displacement	< 3. 10 ¹⁴		< 400°C	MICA / CALIPSO
	Accident tolerance						LORELEI (fuel)

MICA test device: "Standard" configuration

- ✓ **MICA** : **M**aterial **I**rradiation **C**apsule
- ✓ Based on **OSIRIS** technologies: CHOUCA / PHAETON
⇒ at least, the same performances
- ✓ Available at JHR start-up
- ✓ Experimental volume:
Upper volume (instrumentation): ϕ 24mm x 2400mm (max.)
Lower volume (instrumentation): ϕ 24mm x 700mm (max.)

"Standard" MICA

- ❖ Static **NaK** coolant
- ❖ $T < 450^{\circ}\text{C}$
- ❖ Many samples
- ❖ Simplified instrumentation: thermocouples

→ Investigation of physical properties of material (vs flux, fluence and temperature) under **high dpa**

MICA test device: “HT” configuration

In the center of a fuel element

- ✓ **MICA** : **M**aterial **I**rradiation **C**apsule
- ✓ Based on **OSIRIS** technologies: CHOUCA / PHAETON
⇒ at least, the same performances
- ✓ Available at JHR start-up
- ✓ Experimental volume:
 - Upper volume (instrumentation): ϕ 24mm x 2400mm (max.)
 - Lower volume (instrumentation): ϕ 24mm x 700mm (max)

“Standard” MICA	“Instrumented” MICA	HT MICA
<ul style="list-style-type: none"> ❖ Static NaK coolant ❖ T < 450°C ❖ Many samples ❖ Simplified instrumentation: thermocouples 	<ul style="list-style-type: none"> ❖ Static NaK coolant ❖ T < 450°C ❖ Specific sample ❖ Evolved instrumentation: thermocouples, LVDT, in-situ loading 	<ul style="list-style-type: none"> ❖ Static inert gas ❖ T > 1000°C ❖ Gen. IV samples ❖ Instrumentation: to be discussed

MICA test device: “Instrumented” configuration

In the center of a fuel element

- ✓ **MICA** : **M**aterial **I**rradiation **C**apsule
- ✓ Based on **OSIRIS** technologies: CHOUCA / PHAETON
⇒ at least, the same performances
- ✓ Available at JHR start-up
- ✓ Experimental volume:
 - Upper volume (instrumentation): ϕ 24mm x 2400mm (max.)
 - Lower volume (instrumentation): ϕ 24mm x 700mm (max)

“Standard” MICA

- ❖ Static **NaK** coolant
- ❖ $T < 450^{\circ}\text{C}$
- ❖ Many samples
- ❖ Simplified instrumentation: thermocouples

“Instrumented” MICA

- ❖ Static **NaK** coolant
- ❖ $T < 450^{\circ}\text{C}$
- ❖ Specific sample
- ❖ Evolved instrumentation: thermocouples, LVDT, in-situ loading

MELODIE experiment

- ✓ Cladding sample
- ✓ In-situ loading: biaxial stress (internal pressure + tensile/compressive load)
- ✓ Scanning diameter gauge and elongation during irradiation

MICA test device: “Instrumented” configuration

- ✓ **MICA** : **M**aterial **I**rradiation **C**apsule
- ✓ MELODIE experiment: To prepare MICA instrumented rigs

- ✓ Successful tests of the online measurement of axial deformations under stress
- ✓ Prototype exhibited already the breakthrough capability to measure a creep rate in a week (several months with « cook-and-look » irradiation devices)
- ✓ Successful tests of the offline measurement of diametral deformations
- ✓ Next step: early 2016 , feedback from this first irradiation campaign, optimise the device (MELODIE2)
- ✓ CEA-VTT investigation for possible irradiation capacity within European Partners to finalise qualification and prepare the Industrial device for JHR

CALIPSO test device

→ Investigation of physical properties of material under **high dpa**

- Thermodynamic loop integrated within the test device
 - Heat Exchanger (HE) / Electrical Heater (EH)
 - Innovative electromagnetic pump (L 450 mm, D 80 mm) → **NaK flow** (2 m³/h)
- Improvement of the sample temperature mastering
 - From 250 up to 450°C (setting of HE & EH parameters)
 - $\Delta\theta < 8^{\circ}\text{C}$ (T_{max} – T_{min} all along the samples stack)

- On-going qualification of the design with a CALIPSO prototype
 - First successful tests of the electromagnetic pump

In the center of a fuel element

OCCITANE test device

Investigation of physical properties after irradiation of NPP pressure vessel steels under **low dpa**

OCCITANE : **O**ut-of-**C**ore **C**apsule for **I**rradiation **T**esting of **A**geing by **N**eutrons

- Static Helium capsule
 - Based on the OSIRIS feedback (IRMA test device, 150 irradiation cycles)
- Ex-core location
 - Fixed location
 - Dose: up to 100 mdpa/y (1 MeV)
 - Neutron shields
- Samples temperature adjustment
 - 230- 300°C
 - Gamma heating
 - Gas gap dimension
 - Electric heating elements
- At least, 18 thermocouples, and 45 dose integrators

- ✓ Equivalent carrying volume: 30x62.5x500mm³
- ✓ **Helium** gas
- ✓ **230 – 300°C** (furnace with 6 heating zones)
- ✓ **100 mdpa/year**

!! Localized corrosion phenomena !!

Need of a corrosion loop to perform integral experiments

- India in-kind contribution (DAE-BARC)
- CEA corrosion loops feedback, MTR+i3 European project
- LWR conditions: well controlled and adjusted water chemistry, temperatures, ...
- Fixed location
 - Ex-core with a large diameter
 - In-core with a smaller diameter (taking into account safety aspect)
- In-situ measurements: ECP, pH, H₂, load, LVDT, cracking propagation, DCPD

Corrosion loop for LWR conditions

JHR facility & experimental capacity: JHR vessel surveillance program

- The vessel is important for safety (2nd nuclear barrier)
- The vessel material (Al 6061) will degrade with time and irradiation
- Therefore we need to understand the change in material properties
- The JHR conditions (spectrum) will be unique, therefore need **SURVEILLANCE SAMPLES**
- Aluminium is susceptible to damage by both thermal (via transmutation) and fast (via DPA) neutrons.
- Therefore need samples both sides of the vessel
- Inside Core (high flux – PROSPERI), outside core (low energy flux – PROSPERO)

Thanks for your attention

JHR facility & experimental capacity: General architecture

Material and fuel irradiation needs in the nuclear industry

Summary for normal conditions

Selection

- Main objectives
 - ✓ Basis irradiation of several innovative products under similar conditions
- Main requirements
 - ✓ High embarking capacity
 - ✓ Few instrumentation
 - ✓ Post irradiation examination

Characterisation

- Main objectives
 - ✓ Measurement of physical properties under neutron flux
 - ✓ Investigation of: Burn-up effect / Fission gas release / Pellet-Clad interaction / Chemical effect / Creep phenomena ...
- Main requirements
 - ✓ High instrumentation
 - ✓ Accurate control of environment conditions (steady or transient)
 - ✓ Single effect experiments

- Parametric irradiations

- ✓ ex: Microstructure effect experiments

Qualification

- Main objectives
 - ✓ Reproduction of environment conditions of power reactors in normal situation
 - ✓ Envelope situations targeted
- Main requirements
 - ✓ Good representativity of power reactor (steady and transient states)
 - ✓ Long term or short term irradiations

MICA test device: “Instrumented” configuration

- ✓ **MICA** : **M**aterial **I**rradiation **C**apsule
- ✓ MELODIE experiment: a challenging experiment in OSIRIS...
..... To prepare MICA instrumented rigs

- Technical goals
 - Study of LWR cladding irradiation creep
 - Real time control of the biaxial stress
+ online measurement of the biaxial creep
- OSIRIS environment
 - Sample holder in a CHOUCA capsule → Similar to MICA capsule
 - 350 °C, static NaK coolant → Similar to MICA capsule
- Biaxial stress controlled in real time
 - Specimen pressurization → Max pressure 160 bar
 - Push-pull axial loading unit
 - Hoop Stress limit: $\sigma_{\theta} = 120$ MPa, Axial stress limit: $\sigma_z = 180$ MPa
- Online biaxial measurement of creep strain
 - Continuous measurement of axial strain with a 5-wire LVDT
 - Periodical measurement of hoop strain with a diameter gauge (DG)

MICA test device: "Instrumented" configuration

✓ **MICA** : **M**aterial **I**rradiation **C**apsule

✓ MELODIE experiment:

In the center of a fuel element

1. Loading module
2. Connecting loading module and lower rig tube
3. Winding of two DG cables
4. Winding of TC7 and TC8 cables
5. Braiding of cables together with SS wire
6. Locking cables to the rig tube
7. Locking cables to the mover posts 1

Espoo, summer 2012

MICA test device: "Instrumented" configuration

- ✓ **MICA** : **M**aterial **I**rradiation **C**apsule
- ✓ MELODIE experiment: To prepare MICA instrumented rigs

In the center of a fuel element

CALIPSO test device

In the center of a fuel element

SOPRANO Facility :

→ Performed first qualification tests with a CALIPSO prototype in 2014

Handling cask

Fluid control panel

Operating platform

→ Good behavior of the components
(electromagnetic pump, heat exchanger, heater)

JHR facility & experimental capacity: Non Destructive Examination (NDE) benches

Sample examination in hot cells

Gamma and X-Ray
tomography systems

Multipurpose test benches

Coupled Gamma & X-ray bench

Test device examination in pools

Neutron imaging system
in reactor pool

Coupled X-ray & γ
bench in reactor pool

Coupled X-ray & γ
bench in storage pool

Neutron Imaging System

Initial checks of the experimental loading
Adjustment of the experimental protocol
On-site NDE tests after the irradiation phase

JHR facility & experimental capacity: First fleet of irradiation material devices

- ✓ follow in the continuity of **OSIRIS** reactor
↳ at least, the same performances
- ✓ Start-up configuration mainly in support to the current NPPs

In-core devices (high dpa rate):

- ✓ ϕ ($E > 1\text{MeV}$) = 2 to $3.7 \cdot 10^{14}$ n/cm²/s ↳ 6 to 9 dpa/year
- ✓ **MICA**:
 - ϕ 24mm x 600mm
 - 3 configurations
 - “Standard”: NaK, $T < 450^\circ\text{C}$, many sample
 - “Instrumented”: NaK, $T < 450^\circ\text{C}$, 1 instrumented sample
 - “HT”: Inert gas, $T > 1000^\circ\text{C}$
- ✓ **CALIPSO**:
 - NaK thermodynamic loop
 - ϕ 24mm x 600mm
 - $250\text{-}450^\circ\text{C}$, $\Delta\theta < 8^\circ\text{C}$

Available at
JHR start-up

Feasibility at
JHR start-up

In reflector devices (low dpa rate):

- ✓ ϕ ($E > 1\text{MeV}$) = 0.2 to $20 \cdot 10^{12}$ n/cm²/s
- ✓ **OCCITANE**:
 - $25 \times 60 \times 470\text{mm}^3$ (at least)
 - $230\text{-}300^\circ\text{C}$
 - Thermocouples, dose integrators
- ✓ **CLOE**:
 - LWR environment
 - Stress loading during irradiation (IASCC)
 - Water chemistry adjustment
 - In-situ measurement

In-kind INDIA
contribution