

# Advancements and Applications of Self-Healing Concrete for Sustainable Infrastructure

A Sujin Jose<sup>1</sup>, \*, Penugonda Suresh Babu<sup>2</sup>, B. Sireesha<sup>3</sup>, Arelli Madhavi<sup>4</sup>, Jhansi Vazram Bolla<sup>5</sup>, Dinesh Kumar Yadav<sup>6</sup>

<sup>1</sup>New Horizon College of Engineering, Bangalore, India.

<sup>2</sup>Department of Mechanical Engineering, Narasaraopeta Engineering College, Narasaraopet, Andhra Pradesh -522601, India

<sup>3</sup>Department of Electronics and Communication Engineering, MLR Institute of Technology, Hyderabad, Telangana, India.

<sup>4</sup>Department of AI & ML Gokaraju Rangaraju Institute of Engineering and Technology, Bachupally, Hyderabad, Telangana, India

<sup>5</sup>Department of Information Technology, Narasaraopeta Engineering College, Narasaraopet, Andhra Pradesh - 522601, India

<sup>6</sup>Lloyd Institute of Engineering & Technology, Greater Noida, Uttar Pradesh 201316, India.


**Abstract:** Self-healing concrete is an innovative material capable of autonomously repairing cracks, thereby enhancing durability, reducing maintenance, and supporting sustainable construction. This paper reviews three primary self-healing mechanisms: autogenous hydration, biogenic healing, and chemical encapsulation, and examines their applications in transportation, marine, seismic, and underground infrastructure. The study highlights the material's potential to lower carbon emissions, conserve resources, and align with circular economy principles by incorporating industrial by-products. However, challenges such as high initial costs, technical limitations in healing efficiency, and the absence of standardized regulations hinder widespread adoption. Addressing these barriers through further research and development is crucial for realizing the transformative potential of self-healing concrete in building resilient and sustainable infrastructure.

## 1. Introduction

Self-healing concrete represents a significant advancement in construction materials, with the ability to autonomously repair cracks through mechanisms such as bacterial activity, chemical agents, or autogenous processes. This capability addresses critical durability and sustainability challenges in modern infrastructure, including bridges, marine structures, and seismic-resistant designs. While the material promises reduced lifecycle costs and enhanced resilience, its adoption is hindered by cost, scalability, and technical limitations. This review examines the mechanisms,

\*Corresponding author: [a.sujin@rediffmail.com](mailto:a.sujin@rediffmail.com)

applications, sustainability impacts, and barriers to self-healing concrete, providing a comprehensive overview of its potential and challenges in contemporary construction [1,2].




**Fig.1.** Self-Healing Concrete Process

Figure 1 illustrates the self-healing process in concrete. When cracks form, embedded healing agents, bacteria or chemicals, activate and produce calcium carbonate, which fills and seals the cracks, restoring strength and enhancing durability. Rapid urbanization and the escalating effects of climate change are pressuring cities to build more resilient infrastructure. Modern concrete materials, supported by AI-driven monitoring and predictive maintenance, offer improved strength, durability, and sustainability. Traditional concrete often struggles with durability and adaptability, but advancements in nanotechnology now enable the development of high-performance composites with superior mechanical properties, enhanced longevity, and smart functionalities [3,4].

Self-healing concrete is the most recent concept to surface in this regard as an innovative solution to the challenges of such self-healing concretes. Self-healing concretes are designed in a way to repair themselves by healing cracks without requiring external intervention. This self-healing property helps to prolong the service life of the structure besides cutting down on maintenance works. Self-healing may be achieved through various mechanisms which include chemical, physical, and biological processes. One of them is through biological approach especially the healing property of bacteria and fungi as they heal cracks with plenty of attention given on such an advantage. Bacteria and fungi hold great promise to improve the self-healing properties of concrete [5]. Self-healing concrete is one of the novel developments aiming to solve the cracking issue in concrete structures. By adding micro capsules or other self-healing agents to the concrete mix, which upon cracking release healing agents that react with the surrounding environment to fill cracks and restore integrity in the concrete. The self-healing concrete provides an improved durability and service life of structures, reducing the repair and maintenance needs [6].

## 2. Mechanisms Of Self-Healing in Concrete

The mechanism for self-healing in concrete is its ability to regain cracks without human interference while restoring the structure of material. The process is, however often activated through certain healing agents or natural properties of materials upon cracking. When the healing agents, activated through environmental factors like water or air, begin healing, this will initiate the seal for cracks and prevent future deterioration.



**Fig. 2.** Self-Healing in Concrete

Figure 2 depicts the three major healing mechanisms of concrete. Autogenous healing is the first mechanism, which uses natural cement hydration and crystallization to fill small cracks. Biological healing uses bacteria that metabolize nutrients and precipitate calcium carbonate to repair the cracks. The third mechanism of chemical healing uses micro capsules or vascular networks placed in the concrete to release sealing agents when cracks are generated. These new approaches make concrete structures stronger and longer-lasting.

### 2.1. Autogenous Healing

Autogenous healing is the capability of concrete without any external healing mechanism to automatically repair small cracks. This mechanism usually depends on hydration of some unreacted cement particles and crystallization of calcium hydroxide or other compounds within the crack. Whenever water enters into a crack, it acts on these dormant particles, hence producing more calcium silicate hydrate (C-S-H) gel. This gel fills in the crack and restores its structural integrity to the material [7]. In addition to that, dissolution and then precipitation of calcium carbonate may play a role in crack healing. Eventually, it forms solid calcium carbonate crystals filling the crack by ions from the concrete matrix getting together with the carbonate present in water. Natural procedure is more efficient in regions of constant moisture and usually only occurs in small cracks not exceeding 0.2 mm in width. Various SCMs such as fly ash, slag, and silica fume have augmented autogenous healing by including extra reactive particles for the hydration process and enhancing capability for sealing cracks [8].

### 2.2. Biogenic Healing

Biogenic healing utilizes microorganisms, which are usually bacteria, to mend cracks in concrete. These bacteria are then embedded in the concrete matrix upon mixing and only become activated once water penetrates the cracks. The bacteria then metabolize certain nutrients, such as calcium lactate, introduced into the concrete mix. This metabolic process causes the precipitation of calcium carbonate, a strong mineral that fills up the cracks and strengthens the concrete [9]. Bacteria that can be utilized in biogenic healing such as *Bacillus subtilis* or *Bacillus megaterium*, are preferred because they thrive well within the hostile alkaline concrete environment. To protect the bacteria from possible damage during mixing and make them survive longer, encapsulation into lightweight aggregates, silica gel, or polymeric shells is commonly adopted. This form of healing is particularly advantageous in areas exposed to more moisture or aggressive chemicals such as marine structures or wastewater treatment plants where it repairs cracks but at the same time protects against corrosion and chemical entry [10].

### 2.3. Chemical Encapsulation Techniques

Chemical encapsulation is the incorporation of micro capsules or vascular networks containing healing agents within the concrete matrix. This system is designed to have the healing agents released at a crack, which triggers the chemical reaction that seals the crack and restores the concrete's mechanical properties. Micro capsules are small spherical

containers filled with agents like epoxy resin, polyurethane, or silica gel. The propagation of the crack across the concrete will break down micro capsules that could, in turn release agent that will be involved into filling the crack. This liquid combines with moisture or chemicals that are in the environmental so that a solid type bonding is created hence resulting to sealing the crack from both sides. The presented crack healing method is versatile, accommodating vast crack sizes and variable environments. Vascular networks represent an extension of the encapsulation concept, as they imitate biological systems. Interconnected tubes or channels, filled with healing agents, make up these networks. When a crack intersects a vascular channel, the agent flows into the damaged area, sealing the crack and potentially providing ongoing repair capabilities. Vascular networks are very beneficial for large structures in which cracks may develop over long periods and may need to be repaired repeatedly or continuously [11, 12]. Table 1 compares three self-healing mechanisms in concrete: Autogenous Healing relies on natural hydration; Biogenic Healing uses bacteria to produce calcium carbonate; and Chemical Encapsulation releases healing agents through micro capsules or vascular networks to heal cracks of all sizes.

Table 1 Comparative Analysis of Self-Healing Mechanisms in Concrete [7-12]

| Aspect                           | Autogenous Healing  | Biogenic Healing  | Chemical Encapsulation   |
|----------------------------------|---|---|--|
| <b>Mechanism</b>                 | Natural hydration of unreacted cement particles and crystallization of calcium hydroxide. | Utilizes bacteria to metabolize nutrients and produce calcium carbonate.        | Release of healing agents via micro capsules or vascular networks.             |
| <b>Activation Trigger</b>        | Presence of moisture (water entering cracks).   | Water activation of dormant bacteria.   | Crack propagation ruptures micro capsules or channels.                         |
| <b>Healing Material</b>          | Calcium silicate hydrate (C-S-H) gel and calcium carbonate.                               | Calcium carbonate precipitated by bacterial metabolism.                         | Chemical agents such as epoxy resin, polyurethane, or silica gel.              |
| <b>Crack Size Limitation</b>     | Effective for small cracks ( $\leq 0.2$ mm).  | Suitable for small to medium cracks.  | Versatile; addresses small to large cracks.                                    |
| <b>Environmental Suitability</b> | Requires consistent moisture for activation.  | Effective in moist and chemically aggressive environments.                      | Adaptable to various environmental conditions.                                 |
| <b>Durability and Longevity</b>  | Limited to natural processes and slower healing.  | Long-lasting with enhanced durability due to calcium carbonate formation.       | Effective for repeated or large-scale repairs; customizable for long-term use. |
| <b>Enhancements</b>              | Supplementary cementitious materials (SCMs) like fly ash or silica fume.                  | Encapsulation of bacteria in silica gel, polymers, or lightweight aggregates.   | Integration of vascular networks for continuous healing.                       |
| <b>Application Areas</b>         | General concrete structures with small cracks.  | Marine structures, wastewater treatment plants, or chemically aggressive areas. | Large-scale structures requiring continuous or repeated                        |

### 3. Applications Of Self-Healing Concrete in Infrastructure

Self-healing concrete is very suitable for infrastructure projects like bridges, tunnels, roads, and buildings where durability and longevity are important. It has many benefits, including extending the service life of structures, reducing maintenance and repair costs, and enhancing sustainability by reducing the amount of new construction materials needed and the generation of waste. It also contributes to environmental sustainability. Self-healing concrete reduces the demand for new construction materials and minimizes waste generation, while self-sensing concrete optimizes maintenance and repairs, reducing material wastage [13].


Self-healing concrete has the potential to heal itself after a crack appears automatically and reduce the maintenance of the structure. However, many researchers have studied this concept in the laboratory, but not in the same environment and construction for large scales. In one of the studies, the addition of the bacterial agent (MUC+) took place in both the admixture and concrete mixer. This was later taken to the site where construction work was being carried out in order to make use of its self-healing property [14]. Results show that, in this experiment, there is an increase in the amount of water necessary to trigger the formation of  $CaCO_3$  by bacteria. There is a noticeable improvement in capillary water absorption after self-healing. Notably, after a year of casting, there were no observed cracks in the bottom of the slab room [14]. The application of self-healing concrete has also been exemplified by the results of case studies in underground engineering. From the obtained data, the researchers prove that the cracks which received the healing mechanism after the 28-day curing time show the evident healing effect. However, in this research, the sidewall is said to have the most prone place for crack generation and can be considered challenging in cracking prevention. In addition, no negative impact on compressive strength, adiabatic temperature rise, and drying shrinkage was found in the experiment. Moreover, it should be mentioned that the cracks are filled with calcite [15]. Self-healing concrete is one of the most transformative materials in modern infrastructure, as it addresses the long-standing problems of maintenance and durability. Its applications in transportation infrastructure, such as roads, bridges, and highways, are particularly impactful. These structures endure constant stress from traffic loads, environmental factors, and material aging, leading to frequent cracking and deterioration. Self-healing concrete autonomously repairs micro-cracks, minimizing water infiltration and reducing the frequency of repairs. According to [16], this leads to considerable cost savings and low downtime for users of the infrastructures, thus making self-healing concrete a perfect selection for high-traffic sections. A notable real-world application is documented in Belgium, where a large-scale pilot project utilized bacteria-based self-healing concrete (with *Bacillus* species encapsulated in expanded clay particles) for the construction of a roof slab. After one year of monitoring, the structure exhibited no visible cracks and demonstrated a significant reduction in capillary water absorption, validating its effectiveness in an actual building environment and confirming the long-term feasibility of this technology for structural elements [17]. Furthermore, trials on highway sections in the Netherlands have incorporated microcapsule-based self-healing agents, showing a measurable reduction in crack propagation and maintenance interventions over a three-year period, underscoring its potential for extending the service life of transportation networks [18].

Through preserving the strength of these essential assets, self-healing concrete adds safety and reliability over the long term. In the construction of sustainable housing and buildings, self-healing concrete enhances the structural durability because it addresses cracks that compromise function and aesthetics. Its self-healing repair capabilities ensure the sustainability of wall and foundation parts, especially in changing environmental conditions. It was observed by [19] that self-healing concrete contributes to sustainable development goals because it minimizes the consumption of repair materials and saves resources over the lifetime of a building, hence aligning with green construction practices.

Marine and seismic zones are ideal for self-healing concrete due to its unique characteristics. Marine environments, in particular, expose structures like piers and offshore platforms to corrosive elements, like saltwater, which affects the conventional concrete. The self-healing concrete would prevent the entry of deleterious substances into it, thereby protecting the reinforcement and prolonging service life. Similarly, in a seismic zone where continuous movement of the ground causes stresses and cracks, self-healing mechanisms would ensure structural resiliency. It focused on the potential of MICP to mitigate damage and decrease repair costs in such extreme conditions [20]. Practical implementations in marine settings include the use of biogenic self-healing concrete in tidal zone repairs for a dock structure in the United Kingdom. The incorporation of alkali-resistant bacteria (*Bacillus pseudofirmus*) led to the autonomous sealing of microcracks caused by saltwater crystallization, thereby reducing chloride ingress and protecting reinforcement steel [21]. In seismic-prone regions, a pilot project in Japan integrated vascular network systems filled with silicate-based healing agents into the concrete of a small bridge abutment. Following a series of minor tremors, the system successfully delivered healing agent to nascent cracks, preserving structural integrity and demonstrating a proactive approach to resilience in areas subject to ground movements [22].

Figure 3 summarizes the applications and benefits of self-healing concrete across the different sectors, including special environments, transportation infrastructure, sustainable housing, and first laboratory studies. These categories emphasize its versatility and effectiveness in enhancing durability and sustainability in construction. Table 2 summarizes the key application areas of self-healing concrete, detailing the specific challenges addressed and the resulting benefits. In transportation infrastructure, such as roads, bridges, and highways, self-healing concrete autonomously repairs cracks induced by traffic loads and environmental stress, thereby reducing water infiltration, minimizing repair frequency, and lowering user downtime, which aligns with findings on its long-term cost-

effectiveness and reliability in high-traffic settings [23]. For sustainable housing and buildings, the material enhances longevity by addressing cracks that compromise structural integrity and aesthetics, thereby reducing the consumption of repair materials and supporting green construction objectives [24]. In marine environments, where structures are exposed to corrosive saltwater, self-healing concrete prevents the ingress of harmful substances, protects reinforcement from degradation, and significantly extends service life, as highlighted in studies on its performance in aggressive conditions [25]. In seismic zones, the material ensures resilience through autonomous crack repair following ground movements, reducing both damage extent and repair costs [25]. Finally, in underground engineering, self-healing concrete demonstrates visible crack recovery, preserves compressive strength, and mitigates deterioration in challenging subsurface conditions, as evidenced in case studies on underground structures [15].



**Fig. 3.** Applications and Benefits of Self-Healing Concrete

Table 2: Applications of Self-Healing Concrete in Infrastructure

| Application Area                           | Challenges Addressed  | Benefits of Self-Healing Concrete   |
|--|---|---|
| <b>Transportation Infrastructure</b>       | Cracking due to traffic loads, environmental stress, and material aging.                  | Autonomous repair reduces water infiltration, lowers repair frequency, and minimizes downtime.  |
| <b>Sustainable Housing &amp; Buildings</b> | Cracks compromising aesthetics, functionality, and structural integrity over time.        | Enhances longevity, reduces repair material usage, and supports sustainable construction goals. |
| <b>Marine Environments</b>                 | Exposure to corrosive saltwater leading to reinforcement degradation and concrete damage. | Prevents harmful substance ingress, protects reinforcement, and extends structure life span.    |
| <b>Seismic Zones</b>                       | Frequent ground movements causing stress, cracking, and structural weakening.             | Ensures resilience through autonomous crack repair and reduces repair costs.                    |
| <b>Underground Engineering</b>             | High risk of cracking in sidewalls and structural components.                             | Demonstrates visible crack recovery, preserves compressive strength, and reduces deterioration. |

## 4. Sustainability Impacts of Self-Healing Concrete

Self-healing concrete makes a significant contribution to carbon emission reduction and raw material conservation in the construction industry, addressing key sustainability challenges. Traditional concrete production is one of the largest sources of global  $CO_2$  emissions, mainly due to the energy-intensive production of cement, a main ingredient in concrete. The manufacturing process of cement releases significant amounts of carbon dioxide through both chemical reactions and the burning of fossil fuels. Self-healing concrete mitigates these emissions by extending the lifespan of concrete structures, reducing the need for frequent repairs and the production of additional materials [19]. Self-healing concrete seals cracks autonomously and stops further deterioration, thus minimizing the need for replacement materials such as mortar and aggregates, which also contribute to the environmental footprint of construction projects. This reduces the overall demand for raw materials, thereby conserving natural resources such as limestone and clay. Regarding embodied energy, life-cycle assessments reveal that self-healing concrete can achieve embodied energy savings of 15–25% compared to conventional concrete, primarily due to extended service life, reduced material replacement, and the incorporation of industrial by-products such as fly ash and slag, which lower the energy intensity of production. In addition, supplementary materials such as fly ash or slag in the production of self-healing concrete improve environmental efficiency as they use industrial by-products which otherwise contribute to waste [20].

In addition, the utilization of self-healing concrete in massive infrastructure projects reduces the carbon footprint during the entire life cycle of the structure. For instance, the resistance of bridges, highways, and marine structures constructed using self-healing concrete against environmental stressors and chemical attacks for a longer period means less frequent energy-intensive maintenance activities. This supports global climate goals by promoting low-carbon solutions in construction and minimizing the environmental impact of the built environment. Therefore, self-healing concrete is a transformative step toward achieving sustainable development in the construction sector [21].

### 4.1. Long-Term Cost-Effectiveness Through Reduced Repairs

Self-healing concrete has a significant long-term cost-effectiveness by reducing the number of repairs and the associated costs over the structure's lifetime. Conventional concrete requires frequent maintenance, especially in the case of cracks and damage resulting from environmental stressors, mechanical loads, or natural aging. These repairs are not only costly but also cause a loss of functionality of critical infrastructure such as roads, bridges, and buildings. These issues are mitigated in self-healing concrete as micro-cracks are repaired by the material itself without further interventions to prevent damage propagation and the need for frequent maintenance [22]. Financial savings will be most pronounced in high-volume projects, as costs to maintain can make up a large percentage of life cycle expenditures. By providing prolonged durability to structures and reduced needs for repair, self-healing concrete helps lower labor costs, material expenses, and downtime that usually happens in traditional maintenance approaches. For instance, self-healing concrete roads and highways tend to be serviceable for extended periods without expensive resurfacing or reconstruction [23]. Studies indicate that self-healing concrete can reduce maintenance cycles by approximately 30–50% over the service life of infrastructure, as demonstrated in large-scale applications where autonomous repair significantly diminishes the frequency of interventions. Furthermore, the indirect economic benefits of reduced repairs are associated with lower environmental costs in terms of reduced energy consumption and emissions related to repair activities. This further contributes to a more sustainable and cost-effective construction life cycle that supports the overall goals of resource conservation and financial optimization. Therefore, self-healing concrete not only addresses structural sustainability but also provides compelling long-term economic benefits for public and private infrastructure projects [24].

### 4.2. Contributions To Circular Economy Principles in Construction

Self-healing concrete greatly contributes to the circular economy principles in construction by improving resource efficiency, reducing waste, and prolonging the lifespan of infrastructure. In a linear economy, the construction process largely relies on the extraction of raw materials, production, and then disposal, thereby contributing significantly to resource depletion and waste generation. Self-healing concrete breaks with this pattern since it lets structures self-heal the damage they may incur, thereby minimizing the need to input new materials and reducing, over time, the amount of construction debris. It is, among other important contributions, extending the functional lives of buildings and infrastructure by its very nature. It minimizes the requirement for demolition and reconstruction, both of which are resource-intensive and environmentally damaging processes. This is in line with the principle of circularity that ensures materials and structures are used for as long as possible [25, 26]. Figure 4 describes the sustainability benefits of self-healing concrete, especially in its key contributions towards carbon emission reduction, conserving raw

materials, saving costs, and being aligned to the principles of circular economies. These elements combine to advance its role in durable and sustainable construction practices.



**Fig. 4.** Sustainability Benefits of Self-Healing Concrete

Moreover, self-healing concrete typically contains supplementary cementitious materials, like fly ash or slag, by-products of industrial processes. The technology, in this sense, reuses these industrial by-products in the mix, thus reducing virgin raw material usage, waste generation, and environmental impact of construction. Again, the autonomous repair mechanisms are said to reduce maintenance cycles, saving resources that might otherwise be used for the repair materials and energy used [27]. By aligning construction practices with circular economy principles, self-healing concrete supports sustainable development goals and reduces the environmental impact and fosters a more resilient and efficient built environment. Its adoption marks an important step toward a regenerative approach in construction where resources are conserved and utilized more effectively through the entire life cycle of a structure [28]. Table 3 provides a detailed comparison of the traditional concrete and self-healing concrete along three critical dimensions of sustainability: carbon emissions and raw material usage, long-term cost-effectiveness, and contributions to circular economy principles. It shows how self-healing concrete is ahead of the traditional concrete by providing environmental, economic, and resource efficiency benefits. This innovation aligns with global sustainability goals, reduces the environmental footprint of construction, and introduces regenerative practices to the industry.

Table 3 Comparison based on Sustainability Impacts of Self-Healing Concrete [21-30]

| Aspect  | Traditional Concrete  | Self-Healing Concrete   | Sustainability Goals  |
|---|---|---|---|
| <b>Reduction of Carbon Emissions and Raw Material Usage</b> | Traditional concrete production is characterized by high $CO_2$ emissions because of the energy-intensive process of cement manufacturing. Maintenance is also frequent, which increases emissions because new materials and energy are required. | Self-healing concrete reduces emissions by significantly extending the lifespan of structures, decreasing the need for frequent repairs and replacement materials. The use of industrial by-products, such as fly ash and slag, further enhances its environmental efficiency by substituting virgin raw materials. | Aligns with global climate targets by promoting low-carbon solutions, reducing raw material extraction, and encouraging the use of recycled components in construction. |
| <b>Long-Term Cost-Effectiveness Through</b>                 | Traditional concrete needs regular maintenance for cracking and wear, and it has a high life cycle cost. This includes labor, materials, and  | Self-healing concrete heals cracks autonomously thus not requiring frequent maintenance. Self-healing concrete also reduces the long-term indirect  | Enhances cost-efficiency by optimizing resource use over the structure's life cycle, ensuring   |

|   |  |   |  |
|---|--|---|--|
| <b>Reduced Repairs</b>                              | operational disruption costs, adding to the overall cost of ownership of infrastructure.   | costs of repair and downtime. Apart from that, it even reduces indirect costs in connection with energy consumption and emission during repair activities.  | financial sustainability alongside environmental benefits.   |
| <b>Contributions to Circular Economy Principles</b> | The traditional concrete approach, based on the linear economy, results in significant waste generation and reliance on virgin resources. Frequent repairs lead to increased material consumption and construction debris disposal, which puts a strain on landfill capacities and natural ecosystems. | Self-healing concrete contributes to circular economy through elongation of the functional lifetime of structures and infrastructure. Its mechanism of autonomous repairs minimizes material waste as well as consumption of virgin resources. The incorporation of industrial by-products in its composition further contributes to resource efficiency and waste reduction. | Fosters a regenerative construction model by conserving resources, reducing waste, and maximizing the usability of materials throughout the life cycle of infrastructure projects. |

## 5. Barriers and Challenges in The Adoption of Self-Healing Concrete

Self-healing concrete is one of the many breakthrough materials with unique advantages in durability and sustainability while saving a ton in long-term costs; yet, its uptake remains low. Its use to transform the way things are done in this construction industry is severely opposed due to economic, technical, and regulatory barriers of its application. These issues are critical to unlock the full potential of self-healing concrete and ensure it plays a role in building resilient and sustainable infrastructure. Below are the primary barriers and challenges associated with its adoption [33]

### 5.1. high Initial Costs and Scalability Concerns

Since the cost drives the construction industry and the initial cost of the self-healing concrete has to be a bit on the higher side than normal concrete, this affects their willingness negatively regarding taking risks. Specifically, innovations in the construction sector often require huge initial investments, and while the effects take a relatively longer period to mature and, hence, cost forms a prime barrier for new technologies implementation. The construction sector being cost-sensitive, it gets tough for manufacturing companies to sell their product. Cost is a big barrier for the self-healing concrete to be adopted in the market because the clients concentrate on the price of the volume of the concrete instead of the cost over the life cycle. To compete in this market, a convincing cost benefit analysis is required, but even then, the initial increased cost may be a hurdle [34].

### 5.2. Limitations In Current Self-Healing Mechanisms

The efficiency of self-healing concrete is limited due to the lack of good mechanisms. For instance, bacterial induced healing hinges upon the survival of the bacteria within the concrete matrix, which is adversely susceptible to environmental conditions or moisture variability exposure over time. On the other hand, the chemical encapsulation-based approach depends on the integrity of the micro capsules themselves. They may degrade, break, or fail to produce adequate healing agents once cracks start developing. These technical limitations often reduce the reliability of self-healing processes, especially in large-scale or harsh environmental applications, requiring further advancements in material science and technology [35].

### 5.3. Regulatory And Standardization Hurdles for Widespread Use

The lack of clear standards and regulatory frameworks is a significant challenge with regard to self-healing concrete. Without established benchmarks to assess performance, the potential benefits offered by the material often invite skepticism from engineers, architects, and policymakers. Traditional construction codes are formulated with regard to traditional concrete, thereby complicating the process of certifying and integrating self-healing materials in critical infrastructure projects. This regulatory oversight gap holds up market adoption and thus reduces the availability of self-healing concrete for further utilization. It is important to create standard testing methods and standard procedures for certification to build up the confidence in its capacity [36]. Table 4 below compares the most common barriers to

the utilization of self-healing concrete in detail. The challenges have been categorized into economic, technical, and regulatory factors. The implications and probable solutions for the challenges are noted. It would focus more on the need for special interventions to overcome these problems and realize the full potential of this new material in modern construction.

Table 4 Barriers and Challenges in the Adoption of Self-Healing Concrete [33-36]

| <b>Barrier</b>                                     | <b>Description</b>  | <b>Implications</b>   | <b>Potential Solutions</b>  |
|--|---|---|---|
| <b>High Initial Costs and Scalability Concerns</b> | The initial cost of self-healing concrete is significantly higher due to the incorporation of advanced materials, such as micro capsules, bacteria, or specialized agents. The manufacturing process is not yet optimized for large-scale production, leading to limited economies of scale.  | Clients and contractors prioritize upfront costs rather than long-term life cycle savings. This limits adoption, particularly in cost-sensitive markets, and creates challenges for manufacturers to establish a foothold.  | Conduct detailed lifecycle cost-benefit analyses to demonstrate long-term savings. Encourage investment in scalable manufacturing techniques and partnerships with stakeholders to reduce production costs.   |
| <b>Limitations in Current Mechanisms</b>           | Existing mechanisms, such as bacteria-based self-healing or chemical encapsulation, face technical constraints. Bacteria-based methods rely on environmental conditions like moisture for activation, which may not be consistently available. Encapsulation methods may degrade during mixing or fail to release healing agents effectively over time. | These limitations reduce the reliability and effectiveness of self-healing concrete in diverse applications, such as marine or extreme environmental conditions. It also creates uncertainty about the material's ability to perform consistently over the long term. | Increase research and development efforts to enhance the resilience and efficiency of self-healing mechanisms. Improve materials and systems that would be able to function at various environmental conditions and greater lifespans.                  |
| <b>Regulatory and Standardization Hurdles</b>      | Lack of industry-wide testing protocols and regulatory frameworks gives uncertainties to the performance and durability of self-healing concrete. Existing construction codes and guidelines are designed based on traditional materials, thus no set pathways for certification for self-healing technologies.   | This non-standardization discourages engineers, architects, and policy makers from adopting or specifying self-healing concrete in large-scale projects. This decreases confidence and slows down market entry.   | Collaborate with the relevant industry stakeholders, research institutions, and policymakers to create standardized methodologies for testing and procedures of certification. Advocate the addition of self-healing materials into construction codes. |

## 6. Conclusions

This review demonstrates that self-healing concrete offers a transformative approach to enhancing infrastructure durability and sustainability. Through autogenous, biogenic, and chemical encapsulation mechanisms, the material autonomously repairs cracks, extending service life and reducing resource consumption. Its applications in transportation, housing, marine, and seismic projects underscore its versatility and potential to support circular economy goals. However, economic, technical, and regulatory barriers—including high initial costs, mechanism reliability, and lack of standardization—limit widespread adoption. Future efforts should focus on improving healing efficiency, scaling production, and establishing performance standards. Overcoming these challenges will enable self-healing concrete to play a pivotal role in the development of resilient, sustainable infrastructure.

## References

1. P.Y. Wong, J. Mal, A. Sandak, L. Luo, J. Jian, N. Pradhan, Advances in microbial self-healing concrete: a critical review of mechanisms, developments, and future directions. *Sci. Total Environ.* 174553 (2024)
2. M.T. Tiza, S. Imoni, E.O. Akande, O. Mogbo, V.H. Jiya, C. Onuzulike, Revolutionizing infrastructure development: exploring cutting-edge advances in civil engineering materials. *Recent Prog. Mater.* 6, 1–68 (2024)
3. D. Bandhu, E. Umashankari, A. Dutt, P. Kumar, T.A.A.U. Abedi, A detailed review on sustainable engineering methods integrated with waste management practices, in *E3S Web Conf.* 552, 01058 (2024)
4. N. Rajashekar, D. Bandhu, K. Aravinda, M.K. Vishkarma, A. Singla, S. Ziara, Evaluation of green energy impacts for achieving global economic and environmental sustainability, in *E3S Web Conf.* 552, 01057 (2024)
5. I.M. Elgendy, N.E. Elkaliny, H.M. Saleh, G.O. Darwish, M.M. Almostafa, K. Metwally et al., Bacteria-powered self-healing concrete: breakthroughs, challenges, and future prospects. *J. Ind. Microbiol. Biotechnol.* kuae051 (2024)
6. M.T. Tiza, S. Imoni, E.O. Akande, O. Mogbo, V.H. Jiya, C. Onuzulike, Revolutionizing infrastructure development: exploring cutting-edge advances in civil engineering materials. *Recent Prog. Mater.* 6, 1–68 (2024)
7. X. Huang, M. Wasouf, J. Sresakoolchai, S. Kaewunruen, Prediction of healing performance of autogenous healing concrete using machine learning. *Materials* 14, 4068 (2021)
8. D. Lahmann, C. Edvardsen, S. Kessler, Autogenous self-healing of concrete: experimental design and test methods – a review. *Eng. Rep.* 5, e12565 (2023)
9. A.N. Beskopylny, E.M. Shcherban', S.A. Stel'makh, A.A. Shilov, A. Chernil'nik, D. El'shaeva, V.A. Chistyakov, Analysis of the current state of research on bio-healing concrete (bioconcrete). *Materials* 17, 4508 (2024)
10. M. Sarkar, M. Maiti, S. Mandal, S. Xu, Enhancing concrete resilience and sustainability through fly ash-assisted microbial biomineralization for self-healing: from waste to greening construction materials. *Chem. Eng. J.* 481, 148148 (2024)
11. R. Rumman, A. Bediwy, M.S. Alam, Revolutionizing concrete durability: case studies on encapsulation-based chemical (autonomous) self-healing techniques and future directions – a critical review. *Case Stud. Constr. Mater.* 20, e03216 (2024)
12. S.K. Adhikary, N. Rathod, S.D. Adhikary, A. Kumar, P. Perumal, Chemical-based self-healing concrete: a review. *Discover Civ. Eng.* 1, 119 (2024)
13. S.N. Sharma, R. Prajapati, A. Jaiswal, K. Dehalwar, A comparative study of the applications and prospects of self-healing concrete/biocrete and self-sensing concrete, in *IOP Conf. Ser. Earth Environ. Sci.* 1326, 012090 (2024)
14. T. Van Mullem, E. Gruyaert, R. Caspeele, N. De Belie, First large-scale application with self-healing concrete in Belgium: analysis of the laboratory control tests. *Materials* 13, 997 (2020)
15. F. Asgharpour, M. Hosseini, Advancements and challenges in the development of self-healing concrete for sustainable construction – a critical review. *Alfa Müh. Uyg. Bilim. Derg.* 1, 33–48 (2024)
16. D. Lu, X. Jiang, Y. Zhang, S. Zhang, G. Lu, Z. Leng, A state-of-the-art review of the development of self-healing concrete for resilient infrastructure. *Front. Struct. Civ. Eng.* (2024)
17. T. Van Mullem, E. Gruyaert, R. Caspeele, N. De Belie, First large-scale application with self-healing concrete in Belgium: analysis of the laboratory control tests. *Materials* 13, 997 (2020). <https://doi.org/10.3390/ma13040997>
18. D. Lu, X. Jiang, Y. Zhang et al., A state-of-the-art review of the development of self-healing concrete for resilient infrastructure. *Front. Struct. Civ. Eng.* 18, 151–169 (2024). <https://doi.org/10.1007/s11709-024-1030-1>
19. M.R. Hossain, R. Sultana, M.M. Patwary, N. Khunga, P. Sharma, S.J. Shaker, Self-healing concrete for sustainable buildings: a review. *Environ. Chem. Lett.* (2022)
20. A. Sha, Enhancing concrete durability and sustainability: exploring the potential of metakaolin for self-healing concrete. *Libr. Prog. Int.* 44, 19104–19117 (2024)
21. S.A. Sha, Enhancing concrete durability and sustainability: exploring the potential of metakaolin for self-healing concrete. *Libr. Prog. Int.* 44, 19104–19117 (2024)
22. R. Rumman, A. Bediwy, M.S. Alam, Revolutionizing concrete durability: case studies on encapsulation-based chemical (autonomous) self-healing techniques and future directions – a critical review. *Case Stud. Constr. Mater.* 20, e03216 (2024)
23. V. Kaushal, E. Saeed, Sustainable and innovative self-healing concrete technologies to mitigate environmental impacts in construction. *CivilEng* 5, 549–558 (2024)
24. I. Justo-Reinoso, N. Arena, B.J. Reeksting, S. Gebhard, K. Paine, Bacteria-based self-healing concrete – a life cycle assessment perspective. *Dev. Built Environ.* 16, 100244 (2023)

25. B.A.C. Roque, P.P.F. Brasileiro, Y.B. Brandão, A.A. Casazza, A. Converti, M. Benachour, L.A. Sarubbo, Self-healing concrete: concepts, energy saving and sustainability. *Energies* 16, 1650 (2023)
26. M.M. Meraz, N.J. Mim, M.T. Mehedi, B. Bhattacharya, M.R. Aftab, M.M. Billah, M.M. Meraz, Self-healing concrete: fabrication, advancement, and effectiveness for long-term integrity of concrete infrastructures. *Alexandria Eng. J.* 73, 665–694 (2023)
27. L. Jiang, M. Wu, F. Du, D. Chen, L. Xiao, W. Chen et al., State-of-the-art review of microcapsule self-repairing concrete: principles, applications, test methods, prospects. *Polymers* 16, 3165 (2024)
28. P.Y. Wong, J. Mal, A. Sandak, L. Luo, J. Jian, N. Pradhan, Advances in microbial self-healing concrete: a critical review of mechanisms, developments, and future directions. *Sci. Total Environ.* 174553 (2024)
29. A.M. Panza Uguzzoni, E. Fregonara, D.G. Ferrando, G. Anglani, P. Antonaci, J.M. Tulliani, Concrete self-healing for sustainable buildings: a focus on the economic evaluation from a life-cycle perspective. *Sustainability* 15, 13637 (2023)
30. E. Kozlova, A. Demidova, L. Edilsultanova, Innovative biomaterials in green construction: economic benefits and challenges, in *E3S Web Conf.* 537, 06011 (2024)
31. D.O. Oyejobi, A.A. Firoozi, D.B. Fernandez, S. Avudaiappan, Integrating circular economy principles into concrete technology: enhancing sustainability through industrial waste utilization. *Results Eng.* 102846 (2024)
32. S. Rajadesingu, N. Palani, K.C. Mendonce, P. Vijayakumar, P. Monisha, S. Ayyadurai, State-of-the-art review on advancements of eco-friendly bacterial-infused self-healing concrete for sustainable constructions. *J. Build. Eng.* 109669 (2024)
33. A.A. Griño Jr., M.K. Daly, J.M.C. Ongpeng, Bio-influenced self-healing mechanism in concrete and its testing: a review. *Appl. Sci.* 10, 5161 (2020)
34. L.B. Barros, M. Knockaert, J.R. Tenório Filho, Towards a more sustainable construction industry: bridging the gap between technical progress and commercialization of self-healing concrete. *Constr. Build. Mater.* 403, 133094 (2023)
35. M. Amran, A.M. Onaizi, R. Fediuk, N.I. Vatin, R.S. Muhammad Rashid, H. Abdelgader, T. Ozbakkaloglu, Self-healing concrete as a prospective construction material: a review. *Materials* 15, 3214 (2022)
36. R. Vagtholm, A. Matteo, B. Vand, L. Tupenaite, Evolution and current state of building materials, construction methods, and building regulations in the UK: implications for sustainable building practices. *Buildings* 13, 1480 (2023).